



GBX Geogrid

Product Type: Integrally Formed Biaxial Geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive Mechanical Interlock
Primary Applications: Base Reinforcement, Subgrade Improvement

PROPERTY	UNIT	GBX-11	GBX-12	GBX-13	GBX-15	GBX-41	GBX-42	GBX-1515	GBX-2020	GBX-3030
□ Index Properties										
Aperture Dimensions (M x X)	in	1.0 x 1.3	1.0 x 1.3	1.65 x 2.36	1.0 x 1.2	1.3x1.3	1.3 x 1.3	1.5x1.5	1.42 x 1.50	1.5x1.5
Minimum Rib Thickness	in	0.03 x 0.03	0.03 x 0.03	0.05 x 0.05	0.07 x 0.06	0.03 x 0.03	0.05 x 0.05	0.035x0.025	0.04 x 0.03	0.09x0.06
Tensile Strength @ 2% Strain	lbs/ft	280 x 450	410 x 620	380x 650	580 x 690	270 x 380	380 x 510	340 x 340	450 x 450	720x720
Tensile Strength @ 5% Strain		580 x 920	810 x 1340	720 x 1200	1200 x 1370	550 x 720	720 x 1,000	750 x 750	890 x 890	1440x1440
Ultimate Tensile Strength		850 x 1300	1310 x 1970	1100 x 1920	1850 x 2050	880 x 920	1400 x 1610	1030 x 1030	1370 x 1370	2055x2055
□ Structural Integrity										
Junction Efficiency	%	93	93	93	93	93	93	93	93	93
Flexural Stiffness	mg-cm	250,000	750,000	450,000	2,000,000	250,000	750,000	325,000	700,000	2,000,000
Aperture Stability	m-N/deg	0.32	0.65	0.58	0.75	0.28	0.48	0.38	0.45	0.75
□ Durability										
Resistance to Installation Damage	%	95/93/90	95/93/90	91/83/72	95/93/90	90/83/70	90/83/75	95/93/90	95/93/90	95/93/90
Resistance to Long Term Degradation		100	100	100	100	100	100	100	100	100
Resistance to UV Degradation		100	100	100	100	100	100	100	100	100
□ Roll Sizes Available										
	ft yd ² lbs	12.95x246 354 yds ²	12.95x164 236yds ²	13.1x164 239yds ²	13.1x164 239yds ²	9.8x246 268yds ²	9.8x164 179yds ²	13.1x246 358yds ²	13.1x246 358yds ²	13.1x164 239yds ²
		13.0x246 355 yds ²	13.0x164 237 yds ²			13.1x246 358yds ²				
		13.10x246 358 yds ²	13.10x164 239yds ²	16x328 583yds ²						

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 12-01-17 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.