



■ FX[®]-HS Series of Nonwoven Geotextiles

Carthage Mills' [FX-HS Series](#) of nonwoven geotextiles are of 100% polypropylene staple fibers which are formed into a random network, needlepunched and heatset for dimensional stability. The [FX-HS Series](#) of nonwoven geotextiles delivers high durability; excellent physical and hydraulic properties; is inert to biological degradation; and resistant to naturally encountered chemicals, alkalis, and acids.

PROPERTY	ASTM TEST	UNIT	FX [®] -30HS	FX [®] -35HS	FX [®] -40HS	FX [®] -45HS	FX [®] -60HS	FX [®] -70HS	FX [®] -80HS	FX [®] -100HS	FX [®] -120HS	FX [®] -160HS	
<input type="checkbox"/> Mechanical													
Grab Tensile Strength	D 4632	lbs	80	90	100	120	160	180	205	250	300	380	
Grab Tensile Elongation		%	50%	50%	50%	50%	50%	50%	50%	50%	50%	50%	
Trapezoidal Tear	D 4533	lbs	30	40	45	50	60	75	80	100	115	140	
CBR Puncture	D 6241		175	250	300	335	410	450	500	625	800	1025	
<input type="checkbox"/> Endurance													
UV Resistance	D 4355	% @ 500 hrs	70%	70%	70%	70%	70%	70%	70%	70%	70%	70%	
<input type="checkbox"/> Hydraulics/Filtration													
Permittivity	D 4491	sec ⁻¹	2.10	2.00	2.00	1.70	1.50	1.40	1.35	0.80	0.80	0.70	
Water Flow Rate		gpm/ft ²	150	145	140	120	110	100	90	75	65	50	
Apparent Opening Size (AOS)	D 4751	US Std Sieve	50	50	70	70	70	70	80	100	100	100	
<input type="checkbox"/> Physical													
Mass Per Unit Area (Typical)	D 5261	oz/yd ²	3.0	3.5	4.0	4.5	6.0	7.0	8.0	10.0	12.0	16.0	
Thickness (Typical)	D 5199	mils	31	34	35	38	48	60	64	80	90	115	
Standard Roll Sizes Packaging Weight	Measured (Typical)	ft yd ²	12.5 ft x 360 ft 500 yd ²										
		lbs	120 lbs	120 lbs	142 lbs	150 lbs	231 lbs	250 lbs	266 lbs	324 lbs	383 lbs	511 lbs	
		ft yd ²	15.0 ft x 360 ft 600 yd ²					15.0 ft x 300 ft ⁽¹⁾ 500 yd ²					
		lbs	135 lbs	160 lbs	167 lbs	198 lbs	203 lbs	231 lbs	254 lbs	347 lbs	383 lbs	463 lbs	

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288-15 and has been replaced with CBR Puncture ASTM D 6241.

- ⁽¹⁾ At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 12-01-16 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.