



■ FX[®]-370MF

Carthage Mills' FX-370MF is a woven High-Performance geotextile produced from high-tenacity polypropylene yarns. FX-370MF is part of the Carthage [FX[®] High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Mechanical/Performance/Design			
Wide Width Tensile Ultimate	ASTM D 4595	52.5 x 47.3 kN/m	3600 x 3240 lbs/ft
Wide Width Tensile @ 5% Strain		21.9 x 22.8 kN/m	1500 x 1560 lbs/ft
Grab Tensile Strength	ASTM D 4632	2.00 x 1.42 kN	450 x 320 lbs
Grab Tensile Elongation		12% x 10%	
<input type="checkbox"/> Endurance			
UV Resistance	ASTM D 4355	80% @ 500 hrs	
<input type="checkbox"/> Hydraulics/Filtration			
Permittivity ⁽¹⁾	ASTM D 4491	0.90 sec ⁻¹	
Water Flow Rate ⁽¹⁾		1630 lpm/m ²	40 gpm/ft ²
Apparent Opening Size (AOS) ⁽¹⁾	ASTM D 4751	0.425 mm	40 US Std. Sieve
<input type="checkbox"/> Physical			
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	4.57 m x 91.5 m 418 m ² 132 kg	15 ft x 300 ft 500 yd ² 290 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics.

- ⁽¹⁾ At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 12-01-16 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.