



## ■ FX<sup>®</sup>-570MF

Carthage Mills' FX-570MF (formerly FX-400MF) is a woven High-Performance geotextile produced from high-tenacity polypropylene yarns. FX-570MF is part of the Carthage [FX<sup>®</sup> High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> <b>Mechanical/Performance/Design</b>	ASTM D 4595		
Wide Width Tensile Ultimate		70.1 kN/m	4800 x 4800 lbs/ft
Wide Width Tensile @ 2% Strain		14.0 x 19.3 kN/m	960 x 1320 lbs/ft
Wide Width Tensile @ 5% Strain		35.0 x 39.4 kN/m	2400 x 2700 lbs/ft
Wide Width Tensile @ 10% Strain		70.1 kN/m	4800 x 4800 lbs/ft
<input type="checkbox"/> <b>Endurance</b>			
UV Resistance	ASTM D 4355	80% @ 500 hrs	
<input type="checkbox"/> <b>Hydraulics/Filtration</b>			
Permittivity <sup>(1)</sup>	ASTM D 4491	0.40 sec <sup>-1</sup>	
Water Flow Rate <sup>(1)</sup>		1222.4 lpm/m <sup>2</sup>	30 gpm/ft <sup>2</sup>
Apparent Opening Size (AOS) <sup>(1)</sup>	ASTM D 4751	0.600 mm	30 US Std. Sieve
<input type="checkbox"/> <b>Physical</b>			
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	4.57 m x 91.4 m 418 m <sup>2</sup> 176 kg	15.0 ft x 300 ft 500 yd <sup>2</sup> 389 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics.

- <sup>(1)</sup> At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
  - The properties reported above are effective 12-01-16 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.