



## FX<sup>®</sup>-MF and TF High-Performance Woven Geotextiles

Carthage Mills' FX- MF and TF Series of High-Performance geotextiles are produced from 100% high-tenacity polypropylene yarns. The Carthage [FX<sup>®</sup> High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

Note: The listing below is a sampling of available products in this Series of High-Performance Geotextiles. For more information and/or a complete listing of all the products in this Series, please call or visit our website.

PROPERTY	ASTM TEST	UNIT	FX <sup>®</sup> -200MF	FX <sup>®</sup> -270MF	FX <sup>®</sup> -270TF	FX <sup>®</sup> -300MF	FX <sup>®</sup> -370MF	FX <sup>®</sup> -375MF	FX <sup>®</sup> -570MF <sup>(1)</sup>	FX <sup>®</sup> -400TF
<input type="checkbox"/> <b>Mechanical/Performance</b>										
Wide Width Tensile Ultimate	D 4595	lbs/ft	2400	2640 x 2460	3179 x 2711	3600	3600 x 3240	3600 x 3300	4800	5070
Wide Width Elongation @ Ult.		%	12 x 8	NP	11.4 x 7.9	15 x 10	NP	NP	NP	10
Wide Width Tensile @ 2%		lbs/ft	240 x 240	480 x 588	290 x 800	480 x 420	540	NP	960 x 1320	NP
Wide Width Tensile @ 5%			780 x 1404	1212 x 1356	1000 x 1700	1392 x 1740	1500 x 1560	1500 x 1560	2400 x 2700	NP
Wide Width Tensile @ 10%			1800 x 2520	NP	2100 x 3000	3180 x 3480	NP	NP	4800	NP
<input type="checkbox"/> <b>Mechanical/Index</b>										
Grab Tensile Strength	D 4632	lbs	320	295 x 260	350 x 350	450 x 350	450 x 320	NP	500 x 475	550
Grab Tensile Elongation		%	15	13% x 12%	20 x 15	15 x 6	12 x 10	NP	11 x 4	17
Trapezoidal Tear	D 4533	lbs	125	110 x 130	120	180 x 140	150 x 160	NP	180	180
CBR Puncture	D 6241		1400	1000	1000	1600	1300	NP	2000	1700
<input type="checkbox"/> <b>Endurance</b>										
UV Resistance	D 4355	% @ 500 hrs	90	80	80	80	80	80	80	80
<input type="checkbox"/> <b>Hydraulics/Filtration</b>										
Permittivity	D 4491	sec <sup>-1</sup>	0.70	0.60	0.15	0.52	0.90	0.52	0.40	0.14
Water Flow Rate		gpm/ft <sup>2</sup>	50	40	11	40	40	40	30	10.5
Apparent Opening Size (AOS)	D 4751	US Std Sieve	40	30	40	30	40	30	30	40
<input type="checkbox"/> <b>Physical</b>										
Standard Roll Sizes Packaging Weight	Measured (Typical)	ft	15 x 300	15 x 300	15 x 300	15 x 300	15 x 300	15 x 300	15 x 300	15 x 300
		yd <sup>2</sup>	500	500	500	500	500	500	500	500
		lbs	275	213	352	325	290	320	389	357
		ft	-	-	17.1 x 327	-	-	-	-	17.1 x 325
		yd <sup>2</sup>	-	-	622	-	-	-	-	614
		lbs	-	-	410	-	-	-	-	448

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288-15 and has been replaced with CBR Puncture ASTM D 6241.

<sup>(1)</sup> Formerly FX-400MF

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-18 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.