



## ■ Carthage 15%™

Carthage 15% is a woven filtration geotextile made of high-tenacity, monofilament polypropylene yarns which are woven into a stable network such that they retain their relative position. Carthage 15% is part of the [Carthage % Open Area Series](#) of woven monofilament filtration geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> <b>Mechanical</b>			
Grab Tensile Strength	ASTM D 4632	1.62 x 0.89 kN	365 x 200 lbs
Grab Tensile Elongation		24% x 10%	
Trapezoidal Tear	ASTM D 4533	0.51 x 0.33 kN	115 x 75 lbs
CBR Puncture	ASTM D 6241	3.00 kN	675 lbs
<input type="checkbox"/> <b>Endurance</b>			
UV Resistance	ASTM D 4355	90% @ 500 hrs	
<input type="checkbox"/> <b>Hydraulics / Filtration</b>			
Permittivity <sup>(1)</sup>	ASTM D 4491	2.10 sec <sup>-1</sup>	
Water Flow Rate <sup>(1)</sup>		5907 lpm/m <sup>2</sup>	145 gpm/ft <sup>2</sup>
Percent Open Area	CW-02215	10-15%	
Apparent Opening Size (AOS) <sup>(1) (2)</sup>	ASTM D 4751	0.425 mm	40 US Std. Sieve
<input type="checkbox"/> <b>Physical</b>			
Standard Roll Sizes / Packaging / Weight (Custom fabrication and packaging are available.)	Measured (Typical)	1.83 m x 91.5 m 167 m <sup>2</sup> 39.6 kg	6.0 ft x 300 ft 200 yd <sup>2</sup> 87.5 lbs
		3.65 m x 91.44 m 334.4 m <sup>2</sup> 79 kg	12.0 ft x 300 ft 400 yd <sup>2</sup> 175 lbs
		3.81 m x 91.44 m 348.39 m <sup>2</sup> 81 kg	12.5 ft x 300 ft 416.7 yd <sup>2</sup> 178 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

(1) At the time of manufacturing. Handling, storage and shipping may change these properties.

(2) AOS, typically referred to as a MARV, is actually reported as a MAXIMUM allowable opening when in English US Sieve units; or as the SMALLEST allowable opening when in Metric units (mm).

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-2022 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.