



■ FX[®]-400TF

Carthage Mills' FX-400TF is a woven High-Performance geotextile produced from high-tenacity polypropylene yarns. FX-400TF is part of the Carthage [FX[®] High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Mechanical/Performance/Design Wide Width Grab Tensile	ASTM D 4595	74.0 x 74.0 kN/m	5070 x 5070 lbs/ft
		Wide Width Grab Elongation	
<input type="checkbox"/> Mechanical/Index Grab Tensile Strength	ASTM D 4632	2.447 kN	550 lbs
		Grab Tensile Elongation	
Trapezoidal Tear	ASTM D 4533	0.801 kN	180 lbs
CBR Puncture	ASTM D 6241	7.560 kN	1700 lbs
<input type="checkbox"/> Endurance UV Resistance	ASTM D 4355	80% @ 500 hrs	
<input type="checkbox"/> Hydraulics/Filtration Permittivity ⁽¹⁾	ASTM D 4491	0.14 sec ⁻¹	
		Water Flow Rate ⁽¹⁾	430 lpm/m ²
Apparent Opening Size (AOS) ⁽¹⁾	ASTM D 4751	0.425 mm	40 US Std. Sieve
<input type="checkbox"/> Physical			
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	4.6 m x 91.4 m 418 m ² 162 kg	15 ft x 300 ft 500 yd ² 357 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288-15 and has been replaced with CBR Puncture ASTM D 6241.

- ⁽¹⁾ At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 12-01-18 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.