



FX[®]-MF High-Performance Woven Geotextiles

Carthage Mills' FX- MF Series of High-Performance geotextiles are produced from 100% high-tenacity polypropylene yarns. The Carthage [FX[®] High-Performance Series](#) of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

Note: The listing below is a sampling of available products in this Series of High-Performance Geotextiles. For more information and/or a complete listing of all the products in this Series, please call or visit our website.

PROPERTY	ASTM TEST	UNIT	FX [®] -270MF	FX [®] -300MF	FX [®] -370MF	FX [®] -375MF	FX [®] -570MF ⁽¹⁾
<input type="checkbox"/> Mechanical/Performance							
Wide Width Tensile Ultimate	D 4595	lbs/ft	2640 x 2460	3600	3600 x 3240	3600 x 3300	4800
Wide Width Elongation @ Ult.		%	NP	NP	NP	NP	NP
Wide Width Tensile @ 2%		lbs/ft	NP	NP	540	NP	960 x 1500
Wide Width Tensile @ 5%			1272 x 1440	1500 x 1560	1500 x 1560	1500 x 1560	2400 x 3000
Wide Width Tensile @ 10%			NP	NP	NP	NP	NP
<input type="checkbox"/> Mechanical/Index							
Grab Tensile Strength	D 4632	lbs	295 x 260	400 x 300	400 x 300	450 x 350	500 x 500
Grab Tensile Elongation		%	13% x 12%	10 x 6	10 x 6	12 x 10	11 x 4
Trapezoidal Tear	D 4533	lbs	110 x 130	135 x 125	135 x 125	150 x 160	180
CBR Puncture	D 6241		1000	1450	1450	1300	2000
<input type="checkbox"/> Endurance							
UV Resistance	D 4355	% @ 500 hrs	80	80	80	80	80
<input type="checkbox"/> Hydraulics/Filtration							
Permittivity	D 4491	sec ⁻¹	0.60	0.52	0.90	0.8	0.50
Water Flow Rate		gpm/ft ²	40	40	60	58	35
Apparent Opening Size (AOS) ⁽²⁾	D 4751	US Std Sieve	30	30	30	30	30
<input type="checkbox"/> Physical							
Standard Roll Sizes Packaging Weight	Measured (Typical)	ft yd ²	15 x 300 500	15 x 300 500	15 x 300 500	15 x 300 500	15 x 300 500
		lbs	213	325	290	320	389

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

(1) Formerly FX-400MF

(2) Maximum Average Roll Value

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-2023 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.