



# ECP-2 10 OZ. Polypropylene Turf Reinforcement Mat

The ECP-2 10 oz. is made with uniformly distributed 100% polypropylene fiber and two medium weight polypropylene nets securely sewn together with UV stabilized thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation.

The ECP-2 10 oz. is a permanent turf reinforcement mat and is suitable for 1:1 slopes and high-flow channels. The ECP-2 10 oz. meets Type 5.A, 5.B specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.18.

<b>Materials:</b>	<b>Netting - Top and Bottom</b>	<b>Matrix</b>	<b>Thread</b>
	Medium weight 5# PMSF UV Stabilized Polypropylene, Black .5" x .5" Opening	100% Green or Tan Polypropylene Fiber	UV Stabilized Black

<b>Roll Sizes:</b>	<b>Standard</b>	<b>"A" Size</b>	<b>Mega</b>
Width:	8.0 ft (2.4 m)	4.0 ft (1.2 m)	16.0 ft (4.6 m)
Length:	112.5 ft (34.3 m)	225.0 ft (68.6 m)	112.5 ft (34.3 m)
Weight $\pm 10\%$ :	62.0 lbs (28.1 kg)	62.0 lbs (28.1 kg)	124.0 lbs (56.2 kg)
Area:	100 yd <sup>2</sup> (83.6 m <sup>2</sup> )	100 yd <sup>2</sup> (83.6 m <sup>2</sup> )	200 yd <sup>2</sup> (167.2 m <sup>2</sup> )
#/Pallet:	16	9	16

**Index Value Properties\*:**

Property	Test Method	Typical
Mass/Unit Area	ASTM D6475	10 oz/yd <sup>2</sup> (339.1 g/m <sup>2</sup> )
Thickness	ASTM D6525	.40 In (10.16 mm)
Tensile Strength-MD	ASTM D6818	370 lb/ft (5.40 Kn/m)
Elongation-MD	ASTM D6818	24 %
Tensile Strength-TD	ASTM D6818	315 lb/ft (4.60 Kn/m)
Elongation-TD	ASTM D6818	20.0 %
Light Penetration	ASTM D6567	25 %
Density / Specific Gravity	ASTM D7912	0.917 g/cm <sup>3</sup>
Water Absorption	ASTM D1117	0 %
Resiliency	ASTM D6524	80 %
UV Resistance	ASTM D4355	82 % (1000 hr)

\* May differ depending upon raw material variations

**Bench-Scale Testing\* (NTPEP\*\*\*):**

Test Method	Parameters	Results
ECTC Method 2 Rainfall	50mm (2in) / hr-30 min	SLR**=4.58
	100mm (4in) / hr-30 min	SLR**=8.80
	150mm (6in) / hr-30 min	SLR**=16.92
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.42 lb/ft <sup>2</sup>
ECTC Method 4 Germination	Top soil; Fescue; 21 day incubation	482% improvement

\*Bench scale tests should not be used for design purposes.  
 \*\*Soil Loss Ratio=Soil Loss Bare Soil/Soil Loss with RECP=1/C-Factor  
 \*\*\* The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product by AASHTO

**Slope Performance Design Values\*:**

Property	Test Method	Value	
<b>C-Factors</b>	ASTM D6459	0.01	
<b>Slope Length (L)</b>	<b>≤ 3:1</b>	<b>3:1-2:1</b>	<b>≥ 2:1</b>
< 50 ft (15m)	0.009	0.019	0.062
50 ft – 100 ft	0.025	0.044	0.077
> 100 ft (30 m)	0.053	0.072	0.096

\*Large-Scale Results obtained by 3<sup>rd</sup> Party GAI Accredited Independent Laboratory

**Channel Performance Design Values\*:**

Property	Test Method	Value
Unvegetated Shear Stress	ASTM D 6460	2.30 lbs/ft <sup>2</sup> (110.12 Pa)
Unvegetated Velocity	ASTM D 6460	9.0 ft/s (2.74 m/s)
Vegetated Shear Stress	ASTM D 6460	10.0 lbs/ ft <sup>2</sup> (478.8 Pa)
Vegetated Velocity	ASTM D 6460	18.0 ft/s (5.49 m/s)
Manning's N (Value Represents a Range)	Calculated	0.024

\*Large-Scale Results obtained by 3<sup>rd</sup> Party GAI Accredited Independent Laboratory

Effective 01/01/19

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.