




CC-4 Double Net Coconut rolled Erosion Control Product

DESCRIPTION

Excel CC-4 consists of a machine produced, clean coconut fiber matrix, manufactured for consistent coverage and thickness. The coconut matrix is confined by a UV stabilized photodegradable, synthetic net on top and bottom, mechanically (stitch) bound on two-inch centers. Excel CC-4 is intended for slope or channel erosion control applications requiring up to thirty-six months of functional longevity. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



CC-4 is made in the USA.

Material Content		
Matrix	Coconut	
Netting	Top and Bottom Net: Medium weight, Synthetic, Regular Degradable	Double Net (black)
Thread	Synthetic, Regular Degradable	

Standard Roll Sizes			
Width	8 ft (2.4 m)	16 ft (4.9 m)	
Length	112 ft (34.1 m)	563 ft (171.0 m)	
Weight ± 10%	56.3 lb (25.6 kg)	563 lb (256.0 kg)	
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)	

Material available in custom roll sizes

Approvals & Classification		
Classification	FHWA: Type 4.B / ECTC: Type 4.B	
TTI Approvals	Class 1 Type B, D	Class 2 Type E,F
NTPEP Number	ECP-2022-01-12	

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.28 in.	(7 mm)
Mass/Unit Area	ASTM D6566	9.0 oz/sy	(305 g/sm)
Tensile Strength – MD	ASTM D6818	280 lbs/ft	(4.1 kN/m)
Tensile Strength – TD	ASTM D6818	180 lbs/ft	(2.6 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	25%	
Density/Specific Gravity	D792	N/A	
Light Penetration	ASTM D6567	15%	
Biomass Improvement	ASTM D7322	500%	
Water Absorption	ASTM D1117	300%	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.02	N/A
Slope Maximum Gradient ¹	1H:1V	N/A
Permissible Shear Stress ²	2.3 psf (110 Pa)	N/A
Permissible Velocity ²	9.0 fps (2.7 m/s)	N/A

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.033	0.031	0.031

1 Maximum Gradient a recommendation for typical installations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Effective 12/01/23

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.