




SR-1RG Single Net Straw Rolled Erosion Control Product

DESCRIPTION

Excel SR-1 Rapid Go (SR-1RG) temporary Erosion Control Blanket (ECB) is composed of 100% weed free agricultural straw matrix mechanically (stitch) bonded on two-inch centers to a single photodegradable, synthetic net. The netting of Excel SR-1RG ECB is treated to accelerate the degradation process. Recommended for applications requiring erosion protection for a period forty-five to ninety days. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



Each roll of Excel SR-1RG is made in the USA.

Material Content	
Matrix	Straw

Netting	Lightweight, Synthetic, Rapid Degradable	Top Net (White/Clear)
---------	--	-----------------------

Thread	Synthetic, Rapid Degradable
--------	-----------------------------

Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	50 lb (22.7 kg)	500 lb (227.0 kg)
Area	100 sy (83.6 m ²)	1000 SY (836.0 m ²)

Material available in custom roll sizes

Approvals & Classification

Classification	FHWA: Type 1.C / ECTC: Type 1.C
TTI Approvals	N/A
NTPEP Number	N/A

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.28 in.	(7 mm)
Mass/Unit Area	ASTM D6566	8.0 oz/sy	(275 g/sm)
Tensile Strength – MD	ASTM D6818	110 lbs/ft	(1.6 kN/m)
Tensile Strength – TD	ASTM D6818	60 lbs/ft	(0.9 kN/m)
Elongation – MD	ASTM D6818	30%	
Elongation – TD	ASTM D6818	30%	
Density/Specific Gravity	D792	N/A	
Light Penetration	ASTM D6567	15%	
Biomass Improvement	ASTM D7322	375%	
Water Absorption	ASTM D1117	400%	

Design Parameters

Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.02	N/A
Slope Maximum Gradient ¹	3H:1V	N/A
Permissible Shear Stress ²	1.6 psf (75 Pa)	N/A
Permissible Velocity ²	5.0 fps (1.5 m/s)	N/A

Manning's n Roughness (HEC-15)

τ_{lower}	τ_{mid}	τ_{upper}
0.040	0.030	0.030

1 Maximum Gradient a recommendation for typical insllations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Effective 12/01/23

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.