




# SS-2RG Double Net Straw Rolled Erosion Control Product

## DESCRIPTION

Excel SS-2 Rapid Go (SS-2RG) temporary Erosion Control Blanket (ECB) is composed 100% weed free agricultural straw mechanically (stitch) bonded on two-inch centers between two photodegradable, synthetic nets. The netting of the SS-2RG ECB is treated to accelerate the degradation process. Excel SS-2RG is recommended for applications requiring erosion protection for a period forty-five to ninety days. The material is fully degradable. The net and thread are photodegradable and the fiber matrix is biodegradable. Actual field longevity is dependent on soil and climatic conditions.



Each roll of Excel SS-2RG is made in the USA.

Material Content	
Matrix	Straw

Netting	Top & Bottom Net: Lightweight, Synthetic, Rapid Degradable	Double Net (White/Clear)
---------	--	--------------------------

Thread	Synthetic, Rapid Degradable
--------	-----------------------------

### Standard Roll Sizes

Width	8 ft (2.4 m)	16 ft (4.9 m)
Length	112 ft (34.1 m)	563 ft (171.0 m)
Weight ± 10%	50 lb (22.7 kg)	500 lb (227.0 kg)
Area	100 sy (83.6 m <sup>2</sup> )	1000 SY (836.0 m <sup>2</sup> )

Material available in custom roll sizes

### Approvals & Classification

Classification	FHWA: Type 1.D / ECTC: Type 1.D
TTI Approvals	N/A
NTPEP Number	N/A

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.30 in.	(8 mm)
Mass/Unit Area	ASTM D6566	8.0 oz/sy	(275 g/sm)
Tensile Strength – MD	ASTM D6818	130 lbs/ft	(1.9 kN/m)
Tensile Strength – TD	ASTM D6818	100 lbs/ft	(1.5 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	25%	
Density/Specific Gravity	D792	N/A	
Light Penetration	ASTM D6567	15%	
Biomass Improvement	ASTM D7322	450%	
Water Absorption	ASTM D1117	400%	

### Design Parameters

Property	Unvegetated	Vegetated <sup>3</sup>
RUSLE C Factor <sup>2</sup>	0.04	N/A
Slope Maximum Gradient <sup>1</sup>	2H:1V	N/A
Permissible Shear Stress <sup>2</sup>	1.8 psf (85 Pa)	N/A
Permissible Velocity <sup>2</sup>	6.0 fps (1.8 m/s)	N/A

### Manning's n Roughness (HEC-15)

$\tau_{lower}$	$\tau_{mid}$	$\tau_{upper}$
0.050	0.036	0.032

1 Maximum Gradient a recommendation for typical installations.

2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

3 Vegetated values dependent on established stand of vegetation

Effective 12/01/23

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.