



■ Carthage 30%™

Carthage 30% is a woven filtration geotextile made of high-tenacity, monofilament polypropylene yarns which are woven into a stable network such that they retain their relative position. Carthage 30% is part of the [Carthage % Open Area Series](#) of woven monofilament filtration geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

PROPERTY	TEST METHOD	DATA	
		MARV	TYPICAL
<input type="checkbox"/> Mechanical			
Grab Tensile Strength	ASTM D 4632	350 x 280 lbs 1.56 x 1.25 kN	370 x 355 lbs 1.64 x 1.57 kN
Grab Tensile Elongation		30% x 18%	37% x 24%
Trapezoidal Tear	ASTM D 4533	100 x 98 lbs 0.44 x 0.43 kN	118 x 127 lbs 0.52 x 0.56 kN
CBR Puncture	ASTM D 6241	870 lbs 3.86 kN	-
<input type="checkbox"/> Endurance			
UV Resistance	ASTM D 4355	90% @ 500 hrs	90% @ 500 hrs
<input type="checkbox"/> Hydraulics / Filtration			
Permittivity ⁽¹⁾	ASTM D 4491	4.0 sec ⁻¹	7.3 sec ⁻¹
Water Flow Rate ⁽¹⁾		300 g/pm/ft ² 12,223 l/min/m ²	550 g/pm/ft ² 22,410 l/min/m ²
Percent Open Area ⁽³⁾	CW-02215	20 - 30%	
Apparent Opening Size (AOS) ^{(1) (2)}	ASTM D 4751	30 US Std. Sieve 0.60 mm	30 US Std. Sieve 0.60 mm
<input type="checkbox"/> Physical			
Standard Roll Sizes / Packaging / Weight (Custom fabrication and packaging are available.)	Measured (Typical)	3.65 m x 91.44 m 334.4 m ² 71.214 kg	12.0 ft x 300 ft 400 yd ² 157 lbs

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

(1) At the time of manufacturing. Handling, storage and shipping may change these properties.

(2) AOS, typically referred to as a MARV, is actually reported as a MAXIMUM allowable opening when in English US Sieve units; or as the SMALLEST allowable opening when in Metric units (mm).

(3) Typical Values

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-2024 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.