



## ■ FX<sup>®</sup>- 2400HSE

Carthage Mills' FX-2400HSE is a nonwoven geotextile designed specifically for the environmental market, is constructed of polypropylene staple fibers which are formed into a random network, needle-punched and heatset for dimensional stability. FX-2400HSE is part of the Carthage **FX<sup>®</sup>-HSE Series** of nonwoven geotextiles, is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

The Carthage Mills' FX-HSE Series of environmental nonwoven geotextiles designates "Mass Per Unit Area" or "Weight Per Square Yard" as a true Minimum value.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> <b>Mechanical</b>			
Grab Tensile Strength	ASTM D 4632	2.225 kN	500 lbs
Grab Tensile Elongation		50%	
Trapezoidal Tear	ASTM D 4533	0.890 kN	200 lbs
CBR Puncture	ASTM D 6241	8.01 kN	1800 lbs
<input type="checkbox"/> <b>Endurance</b>			
UV Resistance	ASTM D 4355	70% @ 500 hrs	
<input type="checkbox"/> <b>Hydraulics / Filtration</b>			
Apparent Opening Size (AOS) <sup>(1,2)</sup>	ASTM D 4751	0.15 mm	100 US Std. Sieve
<input type="checkbox"/> <b>Physical</b>			
Mass Per Unit Area	ASTM D 5261	814 g/m <sup>2</sup>	24.0 oz/yd <sup>2</sup>
Thickness	ASTM D 5199	5.1 mm	200 mils
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	4.5 m x 46 m 209 m <sup>2</sup>	15 ft x 150 ft 250 yd <sup>2</sup>

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- <sup>(1)</sup> At the time of manufacturing. Handling, storage and shipping may change these properties.
- <sup>(2)</sup> Maximum Average Roll Value
  - Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
  - The properties reported above are effective 01-01-26 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.