



■ FX[®]-270TF

Carthage Mills' FX-270TF is a woven High-Performance geotextile produced from high-tenacity polypropylene yarns. FX-270TF is part of the Carthage **FX[®] High-Performance Series** of woven geotextiles, is inert to biological degradation, and resistant to naturally encountered chemicals, alkalis and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Mechanical/Performance/Design	ASTM D 4595		
Wide Width Tensile Ultimate		46.0 x 40.0 kN/m	3179 x 2711 lbs/ft
Wide Width Elongation		11.4% x 7.9%	
Wide Width Tensile @ 2% Strain		4.2 x 12.7 kN/m	287 x 871 lbs/ft
Wide Width Tensile @ 5% Strain		14.6 x 26.4 kN/m	1085 x 1812 lbs/ft
Wide Width Tensile @ 10% Strain		39.4 x - kN/m	2700 x - lbs/ft
<input type="checkbox"/> Mechanical/Index	ASTM D 4632		
Grab Tensile Strength		1.56 x 1.56 kN	350 x 350 lbs
Grab Tensile Elongation		20% x 15%	
Trapezoidal Tear	ASTM D 4533	0.53 x 0.53 kN	120 x 120 lbs
CBR Puncture	ASTM D 6241	4.44 kN	1000 lbs
<input type="checkbox"/> Endurance	ASTM D 4355		
UV Resistance		80% @ 500 hrs	
<input type="checkbox"/> Hydraulics/Filtration	ASTM D 4491		
Permittivity ⁽¹⁾		0.15 sec ⁻¹	
Water Flow Rate ⁽¹⁾		448 lpm/m ²	11 gpm/ft ²
Apparent Opening Size (AOS) ⁽¹⁾	ASTM D 4751	0.425 mm	40 US Std. Sieve
<input type="checkbox"/> Physical	Measured (Typical)		
Standard Roll Sizes / Packaging / Weight		4.57 m x 91.4 m 418 m ² 102.5 kg	15.0 ft x 300 ft 500 yd ² 226 lbs
	5.21 m x 80.1 m 520 m ² 129.27 kg	17.1 ft x 327 ft 622 yd ² 285 lbs	

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- ⁽¹⁾ At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
 - The properties reported above are effective 01-01-19 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.