



■ FX® Slit-Film Series of Woven Geotextiles

Carthage Mills [FX® Slit-Film Series](#) of woven geotextiles are made of high-tenacity polypropylene yarns woven into a stable network. The [FX® Slit-Film Series](#) of woven geotextiles achieves higher tensile strengths at low elongation (high modulus); is inert to biological degradation; and resistant to naturally encountered chemicals, alkalis, and acids.

PROPERTY	METHOD	UNIT	FX®-22 ⁽¹⁾ (typical)	FX®-55	FX®-60	FX®-66
<input type="checkbox"/> Mechanical						
Grab Tensile Strength	ASTM D 4632	lbs	153 x 149	200	250	315
Grab Tensile Elongation		%	20%	15%	15%	15%
Trapezoidal Tear	ASTM D 4533	lbs	62	75	90	120
CBR Puncture	ASTM D 6241		549	700	750	900
<input type="checkbox"/> Endurance						
UV Resistance	ASTM D 4355	% @ 500 hrs	90%	70%	70%	70%
<input type="checkbox"/> Hydraulics / Filtration						
Permittivity	ASTM D 4491	sec ⁻¹	0.09	0.05	0.05	0.05
Water Flow Rate		gpm/ft ²	7	4	4	4
Apparent Opening Size (AOS)	ASTM D 4751	US Std Sieve	50-60	40	40	40
<input type="checkbox"/> Physical						
Standard Roll Sizes	Measured (Typical)	ft (yd ²)	12.5 x 504 (700 yd ²) 15 x 420 (700 yd ²) 17.5 x 360 (700 yd ²)	12.5 x 432 (600 yd ²) 15.0 x 360 (600 yd ²) 17.5 x 309 (600 yd ²)	12.5 x 432 (600 yd ²) 15.0 x 360 (600 yd ²) 17.5 x 309 (600 yd ²)	12.5 x 360 (500 yd ²) 15.0 x 300 (500 yd ²) 17.5 x 258 (500 yd ²)

NOTES: Mullen Burst Strength ASTM D 3786 is no longer recognized by ASTM D35 on Geosynthetics. Puncture Strength ASTM D 4833 is not recognized by AASHTO M 288 and has been replaced with CBR Puncture ASTM D 6241.

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV); are calculated as the Typical minus two standard deviations; and are based on a 97.7% confidence level.
- The properties reported above are effective 01/01/24 and subject to change without notice.

1. This is a Special Order Item

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.