



■ GBX Geogrid

Product Type: Integrally Formed Biaxial Geogrid
Polymer: Polypropylene
Load Transfer Mechanism: Positive Mechanical Interlock
Primary Applications: Base Reinforcement, Subgrade Improvement

PROPERTY	UNIT	GBX-11	GBX-12	GBX-13	GBX-15	GBX-41
□ Index Properties						
Aperture Dimensions (M x X)	in	1.0 x 1.3	1.0 x 1.3	1.8 x 2.5	1.0 x 1.2	1.5x1.5
Minimum Rib Thickness	in	0.03 x 0.03	0.05 x 0.05	0.05 x 0.05	0.07 x 0.06	0.035 x 0.025
Tensile Strength @ 2% Strain	lbs/ft	280 x 450	410 x 620	380x 650	580 x 690	340 x 340
Tensile Strength @ 5% Strain		580 x 920	810 x 1340	720 x 1200	1200 x 1370	750 x 750
Ultimate Tensile Strength		850 x 1300	1310 x 1970	1100 x 1920	1850 x 2050	1030 x 1030
□ Structural Integrity						
Junction Efficiency	%	93	93	93	93	93
Flexural Stiffness	mg-cm	250,000	750,000	450,000	2,000,000	325,000
Aperture Stability	m-N/deg	0.32	0.65	0.58	0.75	0.38
□ Durability						
Resistance to Long Term Degradation	%	100	100	100	100	100
Resistance to UV Degradation		98	98	98	98	98
□ Roll Sizes Available						
Call for Roll Sizes						

- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV).
- The properties reported above are effective 01-01-26 and are subject to change without notice.

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.