




PP5-12 Double Net Polypropylene Turf Reinforcement Mat

DESCRIPTION

Excel PP5-12 Turf Reinforcement Mat (TRM) is composed of 100% synthetic green fibers mechanically (stitch) bound between two UV stabilized, synthetic nets. Stitching is secured on two-inch centers using UV stabilized, synthetic thread. Excel PP5-12 is a permanent, three-dimensional TRM that provides immediate erosion protection and long-term turf reinforcement and is intended for applications requiring erosion protection for greater than thirty-six months. Each roll of Excel PP5-12 is made in the USA.



Material Content	
Matrix	Synthetic Fibers
Netting	Top Net: Mediumweight, UV stable
	Bottom Net: Mediumweight, UV stable
Thread	Synthetic, UV Stable

Standard Roll Sizes				
Width	8 ft	(2.4 m)	16 ft	(4.9 m)
Length	112 ft	(34.0 m)	112 ft	(34.0 m)
Weight ± 10%	75 lb	(34.0 kg)	150 lb	(68.0 kg)
Area	100 sy	(83.6 m ²)	200 SY	(167.0 m ²)

Material available in custom roll sizes

Approvals & Classification	
Classification	FHWA: Type 5.C / ECTC: 5.D
TTI Approvals	Class 2 Type H
NTPEP Number	ECP-2020-01-009

Index Property	Test Method	Typical	
Thickness	ASTM D6525	0.40 in.	(10 mm)
Mass/Unit Area	ASTM D6566	12.0 oz/sy	(400 g/sm)
Tensile Strength – MD	ASTM D6818	325 lbs/ft	(4.7 kN/m)
Tensile Strength – TD	ASTM D6818	225lbs/ft	(3.3 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	30%	
UV Stability	ASTM D4355	80% @1000 hr	
Light Penetration	ASTM D6567	20%	
Biomass Improvement	ASTM D7322	400%	
Specific Gravity	ASTM D792	57.4 lb/ft ³	(0.92 g/cm ³)
Porosity	ECTC	96%	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	0.03	N/A
Slope Maximum Gradient ¹	0.5H:1V	0.5H:1V
Permissible Shear Stress ²	2.8 psf (135 Pa)	12.0 psf (575 Pa)
Permissible Velocity ²	9.0 fps (2.7 m/s)	18.0 fps (5.5 m/s)
τ_{veg} / τ_{TRM} (HEC-15)	N/A	0.55

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.041	0.033	0.028

1 Maximum Gradient a recommendation for typical installations.
 2 Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.
 3 Vegetated values dependent on established stand of vegetation

Effective 12/01/23

Carthage Mills assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Carthage Mills disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.